

Technical Data Sheet

JACKOCELL® R 312

2016-11-14

Expandable Polystyrene

Doc.-Nr. 016-11-5004

Trade name

JACKOCELL® R 312

Polymer

Polystyrene 100%

Blowing Agent

Total pentane content > 6%

Bulk density

610 ± 30 kg/m³

Bead size range

0,7 - 1,0 mm diameter

Bead size distribution

> 1,25 mm = max 0,5%
< 0,50 mm = max 0,3%

Coefficient of variation

< 15%

Application

Normal shape moulding
Block moulding

Recommended minimum ageing time
of pre-expanded beads

4 hours

Recommended minimum density

18 g/l (kg/m³)

Special features

Fast moulding cycles
High strength

Conditions of storage and preservation

For EPS to keep all characteristics, we advise to store the containers dry and at ambient temperature.

In these conditions and in an unopened original IBC we would recommend using the material within 3 months of the production date.

Packaging

JACKOCELL® is available in 1100 kg IBC.

Safety

EPS may produce flammable vapours.

Thus:

- only store in well ventilated premises.
- no fire nor sparks in the vicinity.
- no smoking nor welding.

Should you require further information see Safety Data Sheet JACKOCELL® expandable polystyrene.



Jackon GmbH, Tonnenhofstrasse 16, D-23970 Wismar/Haffeld, Germany / Phone +49 3841 420 0, Fax +49 3841 420 420 / www.jackon.de / info@jackon.de

Jackon GmbH guarantees that the product meets the specification above. The keeping, handling and use of the products are beyond the control of Jackon GmbH, and therefore shall not invoke any responsibility of the company. This TD substitutes and deletes all previous.